

UNCLASSIFIED

AD NUMBER

AD489140

LIMITATION CHANGES

TO:

Approved for public release; distribution is unlimited.

FROM:

Distribution authorized to U.S. Gov't. agencies and their contractors;  
Administrative/Operational Use; FEB 1966. Other requests shall be referred to Air Force Material Labs., Wright-Patterson AFB, OH 45433.

AUTHORITY

AFSC ltr 21 Mar 1989

THIS PAGE IS UNCLASSIFIED

Not in 489140  
AFML-TR-65-2  
Part II, Volume IX

489140

AD No.

DOC FILE COPY

TERNARY PHASE EQUILIBRIA IN TRANSITION METAL-  
BORON-CARBON-SILICON SYSTEMS

Part II. Ternary Systems

Volume IX. Zr-W-B System and the Pseudobinary  
System  $TaB_2$ - $HfB_2$

Y. A. Chang

February 1966

This document is subject to special export controls, and each transmittal to foreign governments or foreign nationals may be made only with prior approval of Metals and Ceramics Division, Air Force Materials Laboratory, Wright-Patterson Air Force Base, Ohio.

Air Force Materials Laboratory  
Research and Technology Division  
Air Force Systems Command  
Wright-Patterson Air Force Base, Ohio

DOC  
RECEIVED  
JAN 19 1966  
E 13

## NOTICES

When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operations, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

Copies of this report should not be returned to the Research and Technology Division unless return is required by security considerations, contractual obligations, or notice on a specific document.

⑥ TERNARY PHASE EQUILIBRIA IN TRANSITION METAL-  
BORON-CARBON-SILICON SYSTEMS -

Part II. Ternary Systems -

Volume IX. Zr-W-B System and the Pseudobinary  
System  $TaB_2-HfB_2$ .

⑨ Technical rept.,

⑩ Y. A. Chang

⑪ Feb 66

⑫ 26p.

⑬ AF 33(615)-1249

This document is subject to special export controls, and each transmittal to foreign governments or foreign nationals may be made only with prior approval of Metals and Ceramics Division, Air Force Materials Laboratory, Wright-Patterson Air Force Base, Ohio.

⑭ AF-7350

⑮ 735001

⑯ AFML

⑰ TR-65-2-Pt-2-Vol-9

mt

(400042)

1473  
act

## FOREWORD

The work described and illustrated in this report was performed at the Materials Research Laboratory, Aerojet-General Corporation, Sacramento, California under USAF Contract No. AF 33(615)-1249. The contract was initiated under Project No. 7350, Task No. 735001. The work was administered under the direction of the Air Force Materials Laboratory, Research and Technology Division with Captain R. A. Peterson and Lt. P.J. Marchiando acting as Project Engineers, and Dr. E. Rudy, Aerojet-General Corporation as Principal Investigator. Professor Dr. Hans Nowotny, University of Vienna, Austria, served as consultant to the project.

The project, which includes the experimental and theoretical investigation of selected refractory ternary systems in the system classes  $Me_1$ - $Me_2$ -C, Me-B-C,  $Me_1$ - $Me_2$ -B, Me-Si-B and Me-Si-C was initiated on 1 January 1964.

The experimental program was laid out by Dr. E. Rudy and the author wishes to thank him for his help in some aspects of this investigation. The many fruitful discussions with D. P. Harmon and J. R. Hoffman are also acknowledged. E. Spencer assisted in the sample preparation, and R. Cobb made the X-ray exposures.

Chemical analyses of the alloys was carried out under the supervision of Mr. W. E. Trahan, Metals and Plastics Chemical Testing Laboratory, Aerojet-General Corporation. The writers also wish to thank Mr. R. Cristoni who prepared the many drawings, and Mrs. J. Weidner who typed the report.

Other reports issued under USAF Contract AF 33(615)-1249 have included:

### Part I. Related Binaries

- Volume I. Mo-C System
- Volume II. Ti-C and Zr-C Systems
- Volume III. Mo-B and W-B Systems
- Volume IV. Hf-C System
- Volume V. Ta-C System. Partial Investigation of the Systems V-C and Nb-C.
- Volume VI. W-C System, Supplemental Information on the Mo-C System.
- Volume VII. Ti-B System
- Volume VIII. Zr-B System
- Volume X. V-B, Nb-B, and Ta-B Systems

### Part II. Ternary Systems

- Volume I. Ta-Hf-C System
- Volume II. Ti-Ta-C System
- Volume III. Zr-Ta-C System
- Volume IV. Ti-Zr-C, Ti-Hf-C, and Zr-Hf-C Systems

## **FOREWORD (Cont'd)**

Volume V. Ti-Hf-B System  
Volume VI. Zr-Hf-B System  
Volume VII. Ti-Si-C, Nb-Si-C, and W-Si-C Systems  
Volume VIII. Ta-W-C System

### **Part III. Special Experimental Techniques**

Volume I. High Temperature Differential Thermal Analysis

### **Part IV. Thermochemical Calculations**

Volume I. Thermodynamic Properties of Group IV, V, and VI Binary Transition-Metal Carbides

Volume II. Thermodynamic Interpretation of Ternary Phase Diagrams

This technical report has been reviewed and is approved.



W. G. RAMKE  
Chief, Ceramics and Graphite Branch  
Metals and Ceramics Division  
Air Force Materials Laboratory

## ABSTRACT

The solid state phase equilibria of the system Zr-W-B at 1400°C and the phase equilibria in the melting range for the four pseudobinary systems:  $\text{ZrB}_2\text{-W}_2\text{B}_3$ ,  $\text{ZrB}_2\text{-WB}$ ,  $\text{ZrB}_2\text{-W}_2\text{B}$  and  $\text{ZrB}_2\text{-W}$  have been investigated using X-ray technique, melting point determinations and metallographic examinations. At 1400°C, the intermetallic phase  $\text{ZrW}_2$  and the four tungsten-boron intermediate phases were found to be in equilibrium with  $\text{ZrB}_2$ . Two ternary phases, one possibly stable only at high temperatures, were indicated to exist in this system.

The pseudobinary system,  $\text{TaB}_2\text{-HfB}_2$  forms a series of continuous solid solutions. The melting points increase smoothly from pure  $\text{TaB}_2$  to  $\text{HfB}_2$ .

# TABLE OF CONTENTS

PAGE

|      |  |    |
|------|--|----|
| I.   | INTRODUCTION AND SUMMARY . . . . .                     | 1  |
| A.   | Introduction . . . . .                                 | 1  |
| B.   | Summary . . . . .                                      | 1  |
|      | 1. Zirconium-Tungsten-Boron . . . . .                  | 1  |
|      | 2. The Pseudobinary System $TaB_2$ - $HfB_2$ . . . . . | 4  |
| II.  | LITERATURE REVIEW . . . . .                            | 4  |
| A.   | Boundary Systems . . . . .                             | 4  |
| B.   | Zirconium-Tungsten Boron . . . . .                     | 7  |
| III. | EXPERIMENTAL PROGRAM . . . . .                         | 8  |
| A.   | Experimental Procedures . . . . .                      | 8  |
|      | 1. Starting Materials . . . . .                        | 8  |
|      | 2. Alloy Preparation and Heat Treatment . . . . .      | 10 |
|      | 3. Melting Points . . . . .                            | 10 |
|      | 4. Metallography . . . . .                             | 12 |
|      | 5. X-ray Analysis . . . . .                            | 13 |
|      | 6. Chemical Analysis . . . . .                         | 13 |
| B.   | Results . . . . .                                      | 13 |
|      | 1. Zirconium-Tungsten-Boron . . . . .                  | 13 |
|      | 2. The Pseudobinary System $TaB_2$ - $HfB_2$ . . . . . | 21 |
| IV.  | DISCUSSION . . . . .                                   | 24 |
| A.   | Zirconium-Tungsten-Boron . . . . .                     | 24 |
| B.   | The Pseudobinary System $TaB_2$ - $HfB_2$ . . . . .    | 25 |
|      | References . . . . .                                   | 26 |



# LIST OF ILLUSTRATIONS

| FIGURE |  | PAGE |
|--------|--|------|
| 1      | The System Zirconium-Tungsten-Boron at 1400°C  | 2    |
| 2      | The Pseudobinary System $\text{ZrB}_2\text{-W}_2\text{B}_5$                                    | 3    |
| 3      | The Constitutional Diagram Zirconium-Tungsten  | 5    |
| 4      | The Constitutional Diagram Zirconium-Boron   | 6    |
| 5      | The Constitutional Diagram Tungsten-Boron  | 7    |
| 6      | The Constitutional Diagram Zirconium-Tungsten-Boron at 1400°C                                  | 8    |
| 7      | Zr-W-B System: Compositions of Solid State Samples   | 11   |
| 8      | Zr-W-B System: Compositions of Melting Point Samples   | 11   |
| 9      | Zr-W-B System: Compositions of Metallographic Samples  | 12   |
| 10     | Phase Equilibria of Zr-W-B System at 1400°C, According to X-ray Analysis                       | 14   |
| 11     | The Phase Diagram for the Pseudobinary System $\text{ZrB}_2\text{-W}_2\text{B}_5$              | 17   |
| 12     | Micrograph of an Arc-Melted Zr-W-B (2/27.5/70.5) Alloy   | 18   |
| 13     | Micrograph of an Arc-Melted Zr-W-B (6/24/70) Alloy   | 18   |
| 14     | Micrograph of an Arc-Melted Zr-W-B (10/35/55) Alloy  | 20   |
| 15     | Micrograph of an Arc-Melted Zr-W-B (3.5/45/51.5) Alloy   | 20   |
| 16     | Micrograph of an Arc-Melted Zr-W-B (13.5/40/46.5) Alloy  | 21   |
| 17     | Lattice Parameters of $(\text{Ta, Hf})\text{B}_2$ Solid Solutions                              | 22   |
| 18     | Compositions (Top) and the Melting Temperatures of $(\text{Ta, Hf})\text{B}_2$ Solid Solutions | 23   |

## LIST OF TABLES

| TABLE |  | PAGE |
|-------|--|------|
| 1     | Experimental Results of Helgorsky, and Chretien and Helgorsky for Zirconium-Tungsten-Boron System at 1400°C. | 9    |
| 2     | Lattice Parameters of the Various Phases in the System Zirconium-Tungsten-Boron                              | 15   |

## I. INTRODUCTION AND SUMMARY

### A. INTRODUCTION

With the advent of rocket-propelled aircraft and missile age, the demand for materials which can withstand high-temperature and corrosive environments is evident. Since the transition metal diborides are high-melting on the one hand and oxidation-resistant on the other, they are potential candidate materials for use as components in composite systems with other materials. Before one can successfully evaluate composite systems, it is necessary to know the interactions between the various diborides themselves and between the diborides and the elemental metals and boron. With this application in mind, the phase diagram for the system zirconium-tungsten-boron and the pseudobinary system hafnium-diboride and tantalum-diboride are investigated in the present study.

### B. SUMMARY

The solid state phase equilibria of the system Zr-W-B at 1400°C and the phase equilibria in the melting range for the four pseudobinary systems:  $ZrB_2-W_2B_5$ ,  $ZrB_2-WB$ ,  $ZrB_2-W_2B$  and  $ZrB_2-W$  were investigated using X-ray method, melting point determinations, and metallographic examination. In a similar manner, the phase equilibrium for the pseudobinary system  $TaB_2-HfB_2$  was also studied.

#### 1. Zirconium-Tungsten-Boron

##### a. Isothermal Section at 1400°C

The intermetallic phase  $ZrW_2$  in the system zirconium-tungsten and the four tungsten-boron intermediate phases:  $W_2B$ ,  $\alpha-WB$ ,  $W_2B_5$ , and  $WB_{n \sim 12}$ , were found to be in equilibrium with  $ZrB_2$  at 1400°C as shown in Figure 1. The solubility of tungsten in  $ZrB_2$  as well as that of zirconium in all the four tungsten-boron intermediate phases are small at this temperature. A ternary phase, which is designated as  $\phi$  and whose

composition and crystal structure were not determined, was found to exist in the region bound by  $\text{ZrB}_2$ , W, and  $\text{ZrW}_2$ . A second ternary phase, which may be stable only at high temperature, was indicated to exist in the region bound by  $\text{ZrB}_2$ , W, and  $\text{W}_2\text{B}$ .




Figure 1. The System Zirconium-Tungsten-Boron at 1400°C.

Presumably, due to the sluggish reaction rate for the formation of these two ternary phases, the  $\phi$ -phase was found always in the presence of  $\text{ZrB}_2$ , W, and  $\text{ZrW}_2$ , and the second ternary phase in the presence of  $\text{ZrB}_2$ , W, and  $\text{W}_2\text{B}$ .

#### b. The Pseudobinary System $\text{ZrB}_2$ - $\text{W}_2\text{B}_5$

The two intermediate phases  $\text{ZrB}_2$  and  $\text{W}_2\text{B}_5$  melt eutectically at  $2230 \pm 20^\circ\text{C}$  with an eutectic composition of  $93 \pm 2$  mole %

$W_2B_5$  as shown in Figure 2. The solubility of zirconium in  $W_2B_5$  is negligible at all temperatures while  $ZrB_2$  dissolves approximately  $13 \pm 3$  mole % of  $W_2B_5$  at the eutectic temperature.




Figure 2. The Pseudobinary System  $ZrB_2$ - $W_2B_5$

- c. The Three Pseudobinary Systems:  $ZrB_2$ -WB,  $ZrB_2$ - $W_2B$ , and  $ZrB_2$ -W.

A cursory investigation of these three pseudobinary systems show that the pseudobinary  $ZrB_2$ -WB melts eutectically at  $2530 \pm 20^\circ\text{C}$  with an eutectic composition approximately 70 mole %

WB;  $\text{ZrB}_2$ - $\text{W}_2\text{B}$  at  $2480 \pm 30^\circ\text{C}$  with an eutectic composition approximately 60 mole %  $\text{W}_2\text{B}$ ; and  $\text{ZrB}_2$ -W at  $2250 \pm 50^\circ\text{C}$  with a eutectic composition approximately 21 mole % tungsten.

## 2. The Pseudobinary System $\text{TaB}_2$ - $\text{HfB}_2$

The two diborides  $\text{TaB}_2$  and  $\text{HfB}_2$  form a series of continuous solid solutions. The lattice parameter 'a' changes linearly with hafnium-exchange while the lattice parameter 'c' shows a slight negative deviation from a linear relationship.

## II. LITERATURE REVIEW

### A. BOUNDARY SYSTEMS

The literature data concerning the phase relationships of the systems zirconium-tungsten, zirconium-boron and tungsten-boron up to 1958 have been summarized and evaluated by Hansen and Anderko<sup>(1)</sup>. According to Hansen and Anderko, one intermediate phase,  $\text{ZrW}_2$ , with a cubic (C 15 type) structure and a lattice parameter of  $a = 7.63 \text{ \AA}$ , exists in the zirconium-tungsten system. This intermediate phase,  $\text{ZrW}_2$ , forms a eutectic with zirconium at approximately  $1660^\circ\text{C}$  and melts peritectically at  $2150^\circ\text{C}$  into tungsten and a melt with 33 atomic % tungsten. The phase diagram zirconium-tungsten taken from Hansen and Anderko, based mainly on the work of Domagala, McPherson, and Hansen<sup>(2)</sup> and Geach and Slattery<sup>(3)</sup>, is shown in Figure 3. More recently, Helgorsky<sup>(4)</sup> found a new phase,  $\text{Zr}_3\text{W}_5$ , in the zirconium-tungsten system. According to Helgorsky, this phase was probably stabilized by the presence of hydrogen. It was found to be stable at  $1400^\circ\text{C}$  in an atmosphere of argon but decomposed to the elements under vacuum. The structure of  $\text{Zr}_3\text{W}_5$  was isotypic with  $\text{W}_5\text{Si}_3$ , and the lattice parameters of  $\text{Zr}_3\text{W}_5$  were,  $a = 9.50 \text{ \AA}$  and  $c = 4.85 \text{ \AA}$ .

According to Hansen and Anderko<sup>(1)</sup>,  $\text{ZrB}_2$  with a hexagonal structure (C 32) melts congruently at  $3040^\circ\text{C}$ . The phase  $\text{ZrB}_{12}$  with a f.c.c. structure stable only at high temperatures melts congruently at  $2680^\circ\text{C}$ , and the third phase, ZrB with a cubic structure of the B-1 type, is stable between




Figure 3. The Constitutional Diagram Zirconium-Tungsten.  
(Hansen and Anderko)

800° to 1250°C. More recent investigations of Rudy and Windisch<sup>(5)</sup> showed that the phase  $ZrB$  does not exist in the zirconium-boron system. According to these authors,  $ZrB_2$  melts congruently at 3245°C with a composition of approximately 66 atomic % boron. The phase  $ZrB_{12}$ , stable at temperatures higher than 1710°C, melts peritectically as shown in Figure 4. The lattice parameters of  $ZrB_2$  were given as  $a = 3.167 \text{ \AA}$ ,  $c = 3.530 \text{ \AA}$ <sup>(5)</sup> and the lattice parameter of  $ZrB_{12}$  is given as  $a = 7.408 \text{ \AA}$ <sup>(5)</sup>.




Figure 4. The Constitutional Diagram Zirconium-Boron  
(Rudy and Windisch)

For the system tungsten-boron, there existed three intermediate phases,  $W_2B$ ,  $WB$ , and  $W_2B_3$  according to Hansen and Anderko<sup>(1)</sup>. The phase  $W_2B$  has a tetragonal structure (C 16) with lattice parameters  $a = 5.564 \text{ \AA}$  and  $c = 4.740 \text{ \AA}$ . Tungsten monoboride is polymorphic. The low-temperature form  $\alpha$ -WB, has a tetragonal structure with lattice parameters  $a = 3.115 \text{ \AA}$  and  $c = 16.93 \text{ \AA}$ ; while the high-temperature form,  $\beta$ -WB, stable above  $1850^\circ\text{C}$ , has an orthorhombic structure with lattice parameters,  $a = 3.19 \text{ \AA}$ ,  $b = 8.40 \text{ \AA}$  and  $c = 3.07 \text{ \AA}$ . The phase  $W_2B_3$  has a hexagonal defect structure with lattice parameters  $a = 2.982 \text{ \AA}$  and  $c = 13.87 \text{ \AA}$ . More recent information concerning the phase relationships of tungsten-boron system have been reviewed by Rudy and Windisch<sup>(6)</sup>. Since the phase equilibria were not entirely established, Rudy and Windisch recently reinvestigated this system and their phase diagram is shown in Figure 5. The above three






Figure 5. The Constitutional Diagram Tungsten-Boron.  
(Rudy and Windisch)

phases were found to melt congruently. In contrast to previous findings, the  $\alpha$ - $\beta$  transformation temperatures for tungsten monoboride phase were found to vary from 2110°C at the tungsten-rich phase boundary to 2170°C at the boron-rich phase boundary. A fourth intermediate phase  $WB_{n/2}$  has a simple hexagonal subcell ( $a = 3.994 \text{ \AA}$  and  $c = 3.174 \text{ \AA}$ ), and melts peritectically at 2020°C.

## B. ZIRCONIUM-TUNGSTEN-BORON

The ternary system zirconium-tungsten-boron at 1400°C was investigated by Helgorsky<sup>(4)</sup> and Chretien and Helgorsky<sup>(7)</sup>. Their findings are summarized in Figure 6 and Table 1. A ternary phase with an undetermined structure was found in the regions F and G (Figure 6). By heating a mixture of  $ZrB_2$  and W in high vacuum between 2075° and 2140°C for several days,

Leitnaker, Bowman and Gilles<sup>(8)</sup> and Leitnaker, Krikorian and Krupka<sup>(9)</sup> found no interaction between these two phases as evidenced by X-ray results. No data concerning the melting range of this system, Zr-W-B, were found in the literature.




Figure 6. The Constitutional Diagram Zirconium-Tungsten-Boron at 1400°C.

(Helgorsky, and Chretien and Helgorsky)

### III. EXPERIMENTAL PROGRAM

#### A. EXPERIMENTAL PROCEDURES

##### 1. Starting Materials

A combination of zirconium diboride, zirconium hydride, tungsten and boron as well as a mixture of zirconium hydride, tungsten and boron powders served as the starting materials for the preparation of all the alloys used in the present investigation.

Table 1. Experimental Results of Helgorsky, and Chretien and Helgorsky for Zirconium-Tungsten-Boron System at 1400°C.

| Region | ZrB <sub>2</sub> | B | WB <sub>4</sub> | W <sub>2</sub> B <sub>5</sub> | WB | W | Zr | W <sub>2</sub> B | ZrW <sub>2</sub> | X |
|--------|------------------|---|-----------------|-------------------------------|----|---|----|------------------|------------------|---|
| A      | x                | x | x               |                               |    |   |    |                  |                  |   |
| B      | x                | x | x               | x                             |    |   |    |                  |                  |   |
| C      | x                |   |                 | x                             | x  | x |    |                  |                  |   |
| D      | x                |   |                 |                               | x  | x |    | x                |                  |   |
| E      | x                |   |                 |                               | x  | x |    | x                | x                |   |
| F      | x                |   |                 |                               |    | x |    | x                | x                | x |
| G      | x                |   |                 |                               |    | x | x  |                  | x                | x |
| H      | x                |   |                 |                               |    | x |    | x                |                  |   |

The zirconium hydride powder, purchased from Wah Chang Corporation, Albany, Oregon, had the following analysis in ppm: Al-67, B-<0.2, C-320, Nb-<100, Cd-<0.3, Co-<5, Cr-125, Cu-<25, Fe-1800, Hf-137, Mg-255, Mn-35, Mo-<10, N-116, Ni-35, O-1300, Pb-15, Si-157, Sn-<10, Ta-<200, Ti-29, V-<5, W-<25, Zn-<50. The hydrogen content was 2.1%.

The tungsten powder purchased from Wah Chang Corporation, Glen Cove, New York, had the following impurities according to chemical analysis in ppm: Al-<0.001, C-<0.002, Ca-<0.001, Co-<0.001, Cr-<0.001, Cm-<0.001, Fe-<0.004, Mg-<0.001, Mn-<0.001, Mo-<0.008, NiM-0.01, O<sub>2</sub>-0.02, Pb-<0.001, Si-<0.001, Sn-<0.001, and Ni-0.0015. The lattice parameter of this starting material determined from a powder pattern using Cr-K $\alpha$  radiation was  $a = 3.163 \text{ \AA}$ . The powder, purchased from United Mineral and Chemical Corporation, had the following analysis: 99.55% B, 0.25% Fe, and 0.08% C.

The zirconium diboride was prepared by directly reacting the elemental metal and boron powders. The resulting diboride had 17.14% boron with a carbon content of 0.16%.

## 2. Alloy Preparation and Heat Treatment

In the present investigation, the cylindrical melting point samples of approximately 13 mm in diameter and 30 mm in length with a rectangular or cylindrical groove in the center were prepared by hot-pressing of well-mixed powder mixtures in graphite dies. Before determining the melting points of these alloys, the hot-pressed samples were ground on sandpaper to remove any minute surface contamination of carbides. A small hole of about 1 mm diameter, drilled on the center portion of the samples, served as the black body cavity for the temperature measurements.


For solid state investigations, the post melting samples as well as freshly hot pressed samples were heat treated at 1400°C under a vacuum of  $< 5 \times 10^{-5}$  mm Hg for a period varying from 100 to 200 hours.

Since the hot-pressed and post melting point samples were in general not sufficiently dense for metallographic examinations, they were arc melted in a non-consumable tungsten electrode melting furnace. The samples were then examined both by X-ray and metallographic technique.


The compositions of the melting point samples, the solid state samples at 1400°C and the metallographic samples are shown in Figures 7 to 9.

## 3. Melting Points

The melting points of the selected alloys for the system Zr-W-B (Figure 8) and the pseudobinary system  $(\text{Ta}, \text{Hf})\text{B}_2$  were determined by the Pirani-technique which has been described in detail in previous publications<sup>(10)</sup>.



**Figure 7. Zr-W-B System: Compositions of Solid State Samples.**



**Figure 8. Zr-W-B System: Compositions of Melting Point Samples.**




Figure 9. Zr-W-B System: Compositions of Metallographic Samples.

The temperature measurements were carried out with a disappearing filament type micropyrometer, which was calibrated against a certified lamp from the National Bureau of Standards. The temperature was corrected for absorption losses in the quartz window of the melting point apparatus and deviations due to non-black body conditions of the observation hole. The detailed treatment with regard to the temperature correction has been described earlier<sup>(10)</sup> and will not be repeated here again.

To prevent any appreciable loss of boron or metal from the melting samples during the course of the melting point determination, the furnace chamber was pressurized to about 2 1/4 atmospheres with high purity helium after a short vacuum degassing treatment at temperatures below the incipient melting points.

#### 4. Metallography

The metallographic samples, which had been either a small portion of the molten zone of the melting point samples or arc-melted

samples, were mounted in an electrically conductive mixture of diallyl-phthalate-lucite-copper powder. After coarse grinding on silicon carbide powder (grit sizes varying between 120 and 600), the samples were first polished on micro-cloth, using a slurry of 0.05 micrometer alumina and chromic acid solution, and then electrolytically etched in 10% oxalic acid solution.

## 5. X-Ray Analysis

Debye-Scherrer powder diffraction patterns, using Cr-K $\alpha$  and Cu-K $\alpha$  radiations, were made of all samples after melting point and solid state investigations, as well as of arc-melted samples for metallographic purposes.

## 6. Chemical Analysis<sup>\*</sup>

The dissolution of alloy powders for boron analysis was achieved by fusion in pre-dried sodium carbonate at 1000°C. The resulting melt was dissolved in water, and excess carbonate removed by barium hydroxide. After removal of the precipitants, boric acid content was determined by differential titration of the boromannitol complex with 10N NaOH between pH values of 5.3 and 8.5. Depending on the sample material, the consistency of data determined by this method varied between  $\pm 0.1$  and  $\pm 1.0$  atomic % boron absolute.

# B. RESULTS

## 1. Zirconium-Tungsten-Boron

### a. Isothermal Section at 1400°C

The phase equilibria shown in Figure 10 for the system Zr-W-B at 1400°C are established based on X-ray analysis of the long time heat treated samples. The four tungsten-boron intermediate phases,

---

<sup>\*</sup>The Chemical Analysis was performed under the supervision of W.E. Trahan, Metals and Plastics Chemical Testing Laboratory of Aerojet-General Corporation




Figure 10. Phase Equilibria of Zr-W-B System at 1400°C, According to X-ray Analysis.

$W_2B$ ,  $\alpha-WB$ ,  $W_2B_5$ , and  $WB_{n \sim 12}$  and the only intermediate phase  $ZrW_2$  in the metal binary are found to be in equilibrium with  $ZrB_2$ . The solubility of tungsten in  $ZrB_2$  as well as that of zirconium in the four tungsten-boron intermediate phases are small based on lattice parameter data (Table 2). For comparison, the lattice parameters of the binary intermediate phases  $ZrB_2$ ,  $W_2B$ ,  $\alpha-WB$ ,  $W_2B_5$ , and  $WB_{12}$  have been reported by Rudy and Windisch<sup>(5,6)</sup>. The solubility of tungsten and boron in zirconium is small based on previous binary phase investigations. On the other hand, there is virtually no solubility of zirconium and boron in tungsten at this temperature since the lattice parameter,  $a = 3.163 \text{ \AA}$  of the tungsten phase is nearly the same as that of pure tungsten  $a = 3.165 \text{ \AA}$ <sup>(11)</sup>.



Table 2. Lattice Parameters of the Various Phases in the System Zirconium-Tungsten-Boron

| Three-Phase Region   | ZrB <sub>2</sub>                  | WB <sub>n</sub>        | W <sub>2</sub> B <sub>5</sub> | α-WB                 | W <sub>2</sub> B     | W        | ZrW <sub>2</sub>   | Zr |
|--|-----------------------------------|------------------------|-------------------------------|----------------------|----------------------|----------|--------------------|----|
| ZrB <sub>2</sub> -WB <sub>n</sub> -W <sub>2</sub> B <sub>5</sub> | a=3.148Å<br>a=3.500Å              | a=3.995Å*<br>c=3.174Å* | a=2.982Å<br>c=13.90Å          |                      |                      |          |                    |    |
| ZrB <sub>2</sub> -W <sub>2</sub> B <sub>5</sub> -α-WB            | a=3.148Å<br>c=3.500Å              |                        | a=2.982Å<br>c=13.83Å          | a=3.115Å<br>c=16.88Å |                      |          |                    |    |
| ZrB <sub>2</sub> -α-WB-W <sub>2</sub> B                          | a=3.164Å <sup>0</sup><br>c=3.530Å |                        |                               | a=3.094Å<br>c=16.96Å | a=5.565Å<br>c=4.740Å |          |                    |    |
| ZrB <sub>2</sub> -W <sub>2</sub> B-W                             | a=3.167Å<br>c=3.526Å              |                        |                               |                      | a=5.565Å<br>c=4.739Å | a=3.163Å |                    |    |
| ZrB <sub>2</sub> -ZrW <sub>2</sub> -Zr                           | a=3.161Å<br>c=3.538Å              |                        |                               |                      |                      | a=7.612Å | a=3.25Å<br>c=5.18Å |    |

\*hexagonal subcell lattice parameters

The phase equilibria at 1400°C in the region bound by  $\text{ZrB}_2$ ,  $\text{ZrW}_2$ , W, and  $\text{W}_2\text{B}$  are not established with certainty in the present investigation due to the sluggish reaction rate of formation of the ternary phase  $\phi$  (Figure 10). X-ray analysis of the melting point samples in the regions  $\text{ZrB}_2$ ,  $\text{ZrW}_2$ , and W showed only the presence of  $\text{ZrB}_2$ ,  $\text{ZrW}_2$ , and W. Upon long time heat treatment of these alloys at 1400°C, a ternary phase  $\phi$  was found in some of these alloys as evidenced by X-ray diffraction patterns of a new and unidentified structure. The intensity of the diffraction pattern of this  $\phi$ -phase is always weak. Moreover, this phase was found only in the presence of  $\text{ZrB}_2$ ,  $\text{ZrW}_2$ , and W. Attempts to prepare single phase alloys of the  $\phi$ -phase were unsuccessful. This  $\phi$ -phase is undoubtedly the same ternary phase found by Helgorsky<sup>(4)</sup> and Chretien and Helgorsky<sup>(7)</sup> in their investigations (Figure 6 and Table 1). Harmon<sup>(12)</sup> also found this phase in the systems Hf-W-B and Hf-Mo-B. The only difference is the composition of this phase in the three different systems.

The second ternary phase whose structure is also unknown, was found in some of the melting point samples within the region  $\text{ZrB}_2$ -W- $\text{W}_2\text{B}$ . The intensity of the diffraction pattern of the second ternary phase is extremely weak. Upon heat treatment of these alloys at 1400°C, the intensity of the diffraction pattern of this phase becomes somewhat weaker. This suggests that this phase may be a high temperature phase. More experimental work is necessary in order to ascertain the compositional and temperature stability ranges of this phase.

#### b. Melting Points of the Pseudobinary Systems

##### (1) $\text{ZrB}_2$ - $\text{W}_2\text{B}_3$ Binary System

The two intermediate phases  $\text{ZrB}_2$  and  $\text{W}_2\text{B}_3$  melt eutectically at  $2230 \pm 20^\circ\text{C}$  as shown in Figure 11. The  $\pm 20^\circ\text{C}$  represents the precision but not the absolute accuracy of the temperature measurements. The eutectic composition is determined to be  $93 \pm 2$  mole %  $\text{W}_2\text{B}_3$  based primarily on metallographic examination of an arc-melted alloy: Zr-W-B (2/27.5/70.5) as shown in Figure 12. The third




Figure 11. The Phase Diagram for the Pseudobinary System  $\text{ZrB}_2$ - $\text{W}_2\text{B}_5$ .

phase present in this alloy is probably the  $\text{WB}_n$  phase since this alloy is on the boron-rich side of the  $\text{ZrB}_2$ - $\text{W}_2\text{B}_5$  pseudobinary. A micrograph of an arc-melted zirconium-rich alloy  $\text{Zr-W-B}$  (6/24/70), as shown in Figure 13, shows the primary crystallization of  $\text{ZrB}_2$ , the eutectic structure, and small amounts of a third phase.




Figure 12. Micrograph of an Arc-Melted Zr-W-B (2/27.5/70.5) X2500 Alloy.

$\text{ZrB}_2$ - $\text{W}_2\text{B}_5$  Eutectic +  $\text{WB}_{n \sim 12}$




Figure 13. Micrograph of an Arc-Melted Zr-W-B (6/24/70) Alloy.

X500

Primary  $\text{ZrB}_2$  +  $\text{ZrB}_2$ - $\text{W}_2\text{B}_5$  Eutectic

The solubility of zirconium in  $W_2B_5$  is negligible at all temperatures based on the fact that the lattice parameters of  $W_2B_5$  in the melting point sample are the same as those of  $W_2B_5$  in the heat treated samples at 1400°C. On the other hand,  $ZrB_2$  dissolves approximately  $13 \pm 3$  mole % of  $W_2B_5$  at the eutectic temperature. The solubility limit at the eutectic temperature is estimated from the lattice parameters of  $ZrB_2$  in the two-phase alloys quenched from 2230°C.

(2) The Three Pseudobinary Systems:  
 $ZrB_2$ -WB,  $ZrB_2$ - $W_2B_5$ , and  $ZrB_2$ -W

The pseudobinary  $ZrB_2$ -WB melts eutectically at  $2530 \pm 20^\circ\text{C}$  with an eutectic composition approximately 70 mole % WB based on the melting point determinations of six alloys and metallographic examination of two arc-melted alloys. Figure 14 shows the  $ZrB_2$ -WB eutectic structure of an arc-melted alloy, Zr-W-B (10/35/55). A micrograph of an arc-melted tungsten-richer alloy, Zr-W-B (35/45/51.5) as shown in Figure 15, shows the primary  $\beta$ -WB in a  $ZrB_2$ -WB eutectic structure. The effect of zirconium addition on the transformation of  $\alpha$ -WB to  $\beta$ -WB and the solubility of zirconium in  $\alpha$ -WB and  $\beta$ -WB were not determined.

The pseudobinary  $ZrB_2$ - $W_2B_5$  also melts eutectically at  $2480 \pm 30^\circ\text{C}$  with a composition of approximately 60 mole %  $W_2B_5$ . Figure 16 shows the  $ZrB_2$ - $W_2B_5$  eutectic structure of an arc-melted Zr-W-B (13.5/40/46.5) alloy. Melting point determinations of nine alloys of the pseudobinary  $ZrB_2$ -W indicates eutectic melting at  $2250 \pm 50^\circ\text{C}$  with a eutectic composition of approximately 21 mole% tungsten. In order to firmly establish the high temperature phase relationships for the three pseudobinary systems,  $ZrB_2$ -WB,  $ZrB_2$ - $W_2B_5$ , and  $ZrB_2$ -W, more experimental work is necessary.



Figure 14. Micrograph of an Arc-Melted Zr-W-B  
(10/35/55) Alloy.

X1500

ZrB<sub>2</sub>-βWB Eutectic Structure.




Figure 15. Micrograph of an Arc-Melted Zr-W-B  
(3.5/45/51.5) Alloy.

X1500

Primary β-WB + ZrB<sub>2</sub>-βWB Eutectic



Figure 16. Micrograph of an Arc-Melted Zr-W-B  
(13.5/40/46.5) Alloy.

X400

$\text{ZrB}_2$ - $\text{W}_2\text{B}$  Eutectic

## 2. The Pseudobinary System $\text{TaB}_2$ - $\text{HfB}_2$

The two diborides  $\text{TaB}_2$  and  $\text{HfB}_2$  form a series of continuous solid solutions at high temperatures as evidenced by X-ray examination. The lattice parameter 'a' changes linearly with hafnium exchange while the lattice parameter 'c' shows a slight negative deviation from a linear relationship as shown in Figure 17. The melting temperatures and the compositions (according to chemical analysis of post-melting samples for boron content) of several diboride samples are shown in Figure 18. The melting points of the pure  $\text{HfB}_2$  and  $\text{TaB}_2$  reported by Rudy and Windisch<sup>(13, 14)</sup> are also included in Figure 18.




Figure 17. Lattice Parameters of (Ta,Hf)B<sub>2</sub> Solid Solutions.






Figure 18. Compositions(Top) and the Melting Temperatures of (Ta,Hf)B<sub>2</sub> Solid Solutions.

#### IV. DISCUSSION

##### A. ZIRCONIUM-TUNGSTEN-BORON

Helgorsky<sup>(4)</sup>, and Chretien and Helgorsky<sup>(7)</sup> investigated the phase equilibria of the system Zr-W-B at 1400°C and found a ternary phase, presumably the  $\phi$ -phase, in regions F and G as shown in Figure 7 and Table 1. However, according to the present investigations, this  $\phi$ -phase does not exist in region G since X-ray diffraction patterns of all the samples in this region show the presence only of Zr,  $\text{ZrB}_2$ , and  $\text{ZrW}_2$ . The composition of this  $\phi$ -phase could not be determined in the present study because of the sluggish kinetics for its formation. As a matter of fact, this  $\phi$ -phase was found only in the presence of  $\text{ZrB}_2$ ,  $\text{ZrW}_2$ , and W. Based on this evidence, it is concluded that this  $\phi$ -phase probably exists in the region bound by  $\text{ZrB}_2$ , W, and  $\text{ZrW}_2$ . Harmon<sup>(12)</sup> also found this ternary phase in the systems Hf-W-B and Hf-Mo-B; however, the compositions of the  $\phi$ -phase in these systems are quite different from that found in the Zr-W-B system.

The four intermediate phases in the tungsten-boron system are in equilibrium with  $\text{ZrB}_2$  at 1400°C, indicating the relatively large stability of  $\text{ZrB}_2$ . As may be expected, the solubility of zirconium in all the tungsten-boron intermediate phases is small due to the large size difference between zirconium and tungsten.

Investigations of the phase relationships in the melting range are limited to the four pseudobinary systems:  $\text{ZrB}_2\text{-W}_2\text{B}_5$ ,  $\text{ZrB}_2\text{-WB}$ ,  $\text{ZrB}_2\text{-W}_2\text{B}$ , and  $\text{ZrB}_2\text{-W}$ . All four systems melt eutectically. X-ray diffraction patterns of the melting samples along the  $\text{ZrB}_2\text{-W}$  pseudobinary show the presence of  $\text{ZrB}_2$ , W,  $\text{W}_2\text{B}$  and a second ternary phase of unknown structure. The intensity of the diffraction pattern of this phase is extremely weak. Upon heat treatment of some of these alloys at 1400°C, the intensity became somewhat weaker, indicating possibly a high-temperature phase. Again, this phase was found by Harmon<sup>(12)</sup> in the systems Hf-W-B and Hf-Mo-B.

## B. THE PSEUDOBINARY SYSTEM $\text{TaB}_2$ - $\text{HfB}_2$ .

One of the criteria for the formation of a series of continuous solid solutions, according to Hume-Rothery, is that the difference between the atomic radii of the two metals must be less than 15%. In the case of the transition metal diboride solid solutions, Post, Glaser, and Moskowitz<sup>(15)</sup> showed that this rule is also valid for the solid solution formation of these diborides. Since the difference between the radii of hafnium and tantalum in  $\text{HfB}_2$  and  $\text{TaB}_2$ , respectively is about 11%, one expects that  $\text{HfB}_2$  and  $\text{TaB}_2$  would form a series of continuous solid solutions. This indeed, is the case. As shown in Figure 18, the lattice parameters 'a' and 'c' increase from pure  $\text{TaB}_2$  to  $\text{HfB}_2$ .

## REFERENCES

1. M. Hansen and K. Anderko: *Constitution of Binary Alloys*, McGraw-Hill Book Company, Inc., New York (1958).
2. R. F. Domagala, D. J. McPherson, and M. Hansen: *Trans. AIME* 197, 73 (1953).
3. G. A. Geach and G. F. Slattery: *Trans. AIME* 197, 747 (1953).
4. J. Helgorsky: *Ann. Chim. (Paris)* 6, 1339 (1961).
5. E. Rudy and St. Windisch: AFML-TR-65-2, Part I. Vol. VIII, (January 1966).
6. E. Rudy and St. Windisch: AFML-TR-65-2, Part I, Vol. III (July 1965).
7. A. Chretien and J. Helgorsky: *Compt. Rend.* 4, 2693 (1961).
8. J. M. Leitnaker, M.G. Bowman, and P.W. Gilles: *J. Electrochem. Soc.* 109, 441-3 (1962).
9. J.M. Leitnaker, N.H. Krikorian, and M.C. Krupka: *J. Electrochem. Soc.* 109, 66 (1962).
10. E. Rudy, St. Windisch, and Y.A. Chang: AFML-TR-65.2, Part I, Vol. I (January 1965).
11. A. Taylor and B. J. Kagle: *Crystallographic Data on Metal and Alloy Structures*, Dover Publications, Inc., New York (1963).
12. D. P. Harmon: AFML-TR-65-2, Part II, (to be issued).
13. E. Rudy and St. Windisch: AFML-TR-65-2, Part I, Vol. IX (Jan 1966).
14. E. Rudy and St. Windisch: AFML-TR-65-2, Part I, Vol. X (1966).
15. B. Post, F. W. Glaser, and P. Moskowitz: *Acta. Met.* 2, 20 (1954).

## DOCUMENT CONTROL DATA - R&amp;D

(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)

|  |  |   |                       |
|--|--|---|-----------------------|
| 1. ORIGINATING ACTIVITY (Corporate author)<br>Materials Research Laboratory<br>Aerojet-General Corporation<br>Sacramento, California   |  | 2a. REPORT SECURITY CLASSIFICATION<br><b>Unclassified</b>                                 |                       |
|  |  | 2b. GROUP<br><b>N/A</b>   |                       |
| 3. REPORT TITLE<br>Ternary Phase Equilibria in Transition Metal-Boron-Carbon-Silicon Systems<br>Part II. Ternary Systems, Vol. IX. Zr-W-B System and the Pseudobinary<br>System $TaB_2-HfB_2$ .  |  |   |                       |
| 4. DESCRIPTIVE NOTES (Type of report and inclusive dates)<br>—   |  |   |                       |
| 5. AUTHOR(S) (Last name, first name, initial)<br><br>Chang, Y. A.  |  |   |                       |
| 6. REPORT DATE<br>February 1966  |  | 7a. TOTAL NO. OF PAGES<br>26  | 7b. NO. OF REFS<br>15 |
| 8a. CONTRACT OR GRANT NO.<br>AF 33(615)-1249   |  | 8a. ORIGINATOR'S REPORT NUMBER(S)<br>AFML TR-65-2<br>Part II. Vol. IX.                    |                       |
| b. PROJECT NO.<br>7350   |  |   |                       |
| c. Task No.<br>735001  |  | 8b. OTHER REPORT NO(S) (Any other numbers that may be assigned<br>this report)<br><br>N/A |                       |
| 10. AVAILABILITY/LIMITATION NOTICES This document is subject to special export controls<br>and each transmittal to foreign governments or foreign nationals may be made<br>only with prior approval of the Air Force Materials Laboratory (MAM), Wright-<br>Patterson Air Force Base, Ohio.  |  |   |                       |
| 11. SUPPLEMENTARY NOTES  |  | 12. SPONSORING MILITARY ACTIVITY<br>AFML (MAMC)<br>Wright-Patterson AFB, Ohio 45433       |                       |
| <p>13. ABSTRACT</p> <p>✓ The solid state phase equilibria of the system Zr-W-B at 1400°C and the phase equilibria in the melting range for the four pseudobinary systems: <math>ZrB_2-W_2B_5</math>, <math>ZrB_2-WB</math>, <math>ZrB_2-W_2B</math> and <math>ZrB_2-W</math> have been investigated using X-ray technique, melting point determinations and metallographic examinations. At 1400°C, the intermetallic phase <math>ZrW_2</math> and the four tungsten-boron intermediate phases were found to be in equilibrium with <math>ZrB_2</math>. Two ternary phases, one possibly stable only at high temperatures, were indicated to exist in this system.</p> <p>The pseudobinary system, <math>TaB_2-HfB_2</math> forms a series of continuous solid solutions. The melting points increase smoothly from pure <math>TaB_2</math> to <math>HfB_2</math>.</p> |  |   |                       |

|  |           |        |    |        |    |        |    |
|--|-----------|--------|----|--------|----|--------|----|
| 14   | KEY WORDS | LINK A |    | LINK B |    | LINK C |    |
|  |           | ROLE   | WT | ROLE   | WT | ROLE   | WT |
| <b>Ternary Borides<br/>High Temperature<br/>Phase Equilibria</b> |           |        |    |        |    |        |    |
|  |           |        |    |        |    |        |    |
|  |           |        |    |        |    |        |    |
|  |           |        |    |        |    |        |    |
|  |           |        |    |        |    |        |    |
|  |           |        |    |        |    |        |    |
|  |           |        |    |        |    |        |    |
|  |           |        |    |        |    |        |    |
|  |           |        |    |        |    |        |    |
|  |           |        |    |        |    |        |    |

### INSTRUCTIONS

**1. ORIGINATING ACTIVITY:** Enter the name and address of the contractor, subcontractor, grantee, Department of Defense activity or other organization (corporate author) issuing the report.

**2a. REPORT SECURITY CLASSIFICATION:** Enter the overall security classification of the report. Indicate whether "Restricted Data" is included. Marking is to be in accordance with appropriate security regulations.

**2b. GROUP:** Automatic downgrading is specified in DoD Directive 5200.10 and Armed Forces Industrial Manual. Enter the group number. Also, when applicable, show that optional markings have been used for Group 3 and Group 4 as authorized.

**3. REPORT TITLE:** Enter the complete report title in all capital letters. Titles in all cases should be unclassified. If a meaningful title cannot be selected without classification, show title classification in all capitals in parentheses immediately following the title.

**4. DESCRIPTIVE NOTES:** If appropriate, enter the type of report, e.g., interim progress, summary, annual, or final. Give the inclusive dates when a specific reporting period is covered.

**5. AUTHOR(S):** Enter the name(s) of author(s) as shown on or in the report. Enter last name, first name, middle initial. If military, show rank and branch of service. The name of the principal author is an absolute minimum requirement.

**6. REPORT DATE:** Enter the date of the report as day, month, year, or month, year. If more than one date appears on the report, use date of publication.

**7a. TOTAL NUMBER OF PAGES:** The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.

**7b. NUMBER OF REFERENCES:** Enter the total number of references cited in the report.

**8a. CONTRACT OR GRANT NUMBER:** If appropriate, enter the applicable number of the contract or grant under which the report was written.

**8b, 8c, & 8d. PROJECT NUMBER:** Enter the appropriate military department identification, such as project number, subproject number, system numbers, task number, etc.

**9a. ORIGINATOR'S REPORT NUMBER(S):** Enter the official report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.

**9b. OTHER REPORT NUMBER(S):** If the report has been assigned any other report numbers (either by the originator or by the sponsor), also enter this number(s).

**10. AVAILABILITY/LIMITATION NOTICES:** Enter any limitations on further dissemination of the report, other than those

imposed by security classification, using standard statements such as:

- (1) "Qualified requesters may obtain copies of this report from DDC."
- (2) "Foreign announcement and dissemination of this report by DDC is not authorized."
- (3) "U. S. Government agencies may obtain copies of this report directly from DDC. Other qualified DDC users shall request through \_\_\_\_\_."
- (4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through \_\_\_\_\_."
- (5) "All distribution of this report is controlled. Qualified DDC users shall request through \_\_\_\_\_."

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indicate this fact and enter the price, if known.

**11. SUPPLEMENTARY NOTES:** Use for additional explanatory notes.

**12. SPONSORING MILITARY ACTIVITY:** Enter the name of the departmental project office or laboratory sponsoring (paying for) the research and development. Include address.

**13. ABSTRACT:** Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical report. If additional space is required, a continuation sheet shall be attached.

It is highly desirable that the abstract of classified reports be unclassified. Each paragraph of the abstract shall end with an indication of the military security classification of the information in the paragraph, represented as (TS), (S), (C), or (U).

There is no limitation on the length of the abstract. However, the suggested length is from 150 to 225 words.

**14. KEY WORDS:** Key words are technically meaningful terms or short phrases that characterize a report and may be used as index entries for cataloging the report. Key words must be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical context. The assignment of links, rules, and weights is optional.

THIS REPORT HAS BEEN DELIMITED  
AND CLEARED FOR PUBLIC RELEASE  
UNDER DOD DIRECTIVE 5200.20 AND  
NO RESTRICTIONS ARE IMPOSED UPON  
ITS USE AND DISCLOSURE.

DISTRIBUTION STATEMENT A

APPROVED FOR PUBLIC RELEASE;  
DISTRIBUTION UNLIMITED.